



Ash

A muffle furnace is used to determine the ash content of paper. We follow TAPPI test methods T-211 (525 °C) and T-413 (900°C).