



AGT (Automated Glue Test)

This is our glue tester that measures the force required to separate the glued pieces. It also allows us to evaluate the amount of fiber tear. We apply a dot of glue of precise thickness, and the tester compresses the samples at a desired pressure for a desired amount of time, then it separates the samples. We run the standard test at 4 minutes time and 20-psig pressure.