



Gloss, 75 Degree

A beam of light is reflected off the surface of the paper or paperboard at 75 deg in the machine direction (MD). The amount of light reflected is compared to a 100% reflective surface. The test result, called the gloss of the product, is the percentage of light reflected.

