



Glue Speed (Pull Tab)

Glue is applied to the backside of a sample with a wire wound rod, the top sample is put into place and compressed. A portion of the sample is separated manually at intervals, and the seconds required to achieve fiber tear is reported.